

R300



Thermal Transfer Ribbon Technical Data Sheet

R300 General Purpose Resin

Product Description

DNP has the most elite resin ribbon offering in the industry. R300's extensive label adaptability and high print speed capability makes it the most diverse resin of its kind. It outperforms the competition in abrasion and solvent resistance, uses less print energy and is designed with DNP's standard anti-static and backcoat properties to protect printheads and extend printhead life. And, like all DNP ribbons, R300 is an industry leader in edge definition producing dark, dense images for improved scan rates.

Recommended Applications





ASSET TRACKING





CHEMICAL DRUM



ELECTRONICCOMPONENT





FLEXIBLE PACKAGING





OUTDOOR



PHARMACEUTICAL









Recommended Substrates

Polypropylene, polyethylene, polyolefin, vinyl, polyester

Performance Characteristics

- Excellent print quality at high speeds using less print energy
- Extreme durability and solvent resistance
- Extensive label adaptability expanding application options
- UL recognized/CSA approved
- Unbeatable edge definition for dark, dense images and improved scan rates
- DNP's specially formulated backcoating for printhead protection
- Most economical resin with DNP's unmatched abrasion resistance
- Anti-static for easy handling and extended printhead life

Visit us at www.dnpribbons.com

DNP Imaging comm America Corporation 1001 Technology Drive • Mt. Pleasant, PA 15666 TEL: 888.569.7222 • FAX: 800.676.7669 www.dnpribbons.com • www.dnpimagingcomm.com **Global Locations** USA Japan **Europe** Asia



R300



Thermal Transfer Ribbon Technical Data Sheet

R300 General Purpose Resin

Ribbon Properties

Result	Test Method
Resin	
Black	Visual
$6.0 \pm 0.5 \mu$	Micrometer
$4.8 \pm 0.3 \mu$	Micrometer
1.2 ± 0.2µ	Micrometer
86°C (187°F)	Differential Scanning Calorimeter
	Resin Black 6.0 ± 0.5µ 4.8 ± 0.3µ 1.2 ± 0.2µ

Durability of Printed Image

Label Stock: Top-coated Polyester Print Speed: 6 IPS

Test Method
Pensitometer
Colorfastness Tester - 100 Cycles @
00 Grams with Cotton Cloth
Colorfastness Tester - 50 Cycles @ 00 Grams with Stainless Steel Pointed Tip
); ()

^{*}American National Standard Institute (ANSI) Grade Levels A, B, C, D, and F, where A is excellent, B is above average, C is average, D is below average, and F is poor.

Conversion Chart

Millimeters (mm) to Inches = mm ÷ 25.4	Inches to Millimeters (mm) = Inches ÷ 0.03937
Meters (m) to Feet (ft) = $m \div 0.3048$	Feet (ft) to Meters (m) = Feet ÷ 3.2808
C° to F° = (1.8 X C°) + 32 = F°	F° to C° = $(F^{\circ} \div 1.8)$ - 17.77
Thousand square inches (MSI) to m ² = MSI X 0.645	$MSI = m^2 \div 0.645$
	,

The information on this data sheet was obtained in DNP laboratories. Measured values may vary slightly when tested in a different environment. Information contained within this document is subject to change without notification.

Visit us at www.dnpribbons.com

DNP Imagingcomm America Corporation 1001 Technology Drive • Mt. Pleasant, PA 15666 TEL: 888.569.7222 • FAX: 800.676.7669 www.dnpribbons.com • www.dnpimagingcomm.com Global Locations
USA
Japan
Europe
Asia